



GOOD2KNOW

– ONsert® Key-facts

BOLLHOFF

Joining technology

Fast and process reliable bonding of fasteners

Adhesive

- One-component acrylate (modified)
- Compliant with RoHS Directive 2017/2102/EU
- Fast curing — full strength within seconds
- Compliant with FAR 25 and ANSI/UL 94

Designs

Plastic-metal versions

ONsert® studs



ONsert® inserts



Plastic versions

ONsert® cable management



ONsert® specials



Materials

Plastic moulding

- PA PACM 12
- PA PACM 12

Metal part*

- Steel with zinc-nickel coating, sizes M5 and M6
- Alloy A286 (passivated, 0.1900-32)
- Alloy EN AW-6061-T6 with X5CrNi18-10HC (1.4301, 0.1900-32)

Plastic

- PA PACM 12
- Bottom part
 - PA PACM 12
- Upper part*
 - PEI
 - PA
- PA PACM 12

Advantages

- Fast curing and immediate strength
- No visual impact on sensitive surfaces
- Applicable if thermal processes cannot be used
- One-component adhesive — no mixing of adhesives
- Manual and automated processing systems available

Limitations

- Permanent ambient temperature < 90 °C
- For metals: AL, steel after e-coating or painting
- For plastics: epoxy-based composites, PC, PA
- For glass: with or without paint

Manual bonding process




Application of the adhesive to the ONsert® fastener



Insertion of the ONsert® fastener into the tool holder



Placing the tool on the substrate



Tool removal and assembly

* Others on request





Parameters

Product type	ONsert® T-stud
Item code	4840 711 0100
Plastic moulding	PA PACM 12
Metal part	–
Surface	–
Adhesive	4839 100 4150
Amount	0.18 g
Tooling	Portable Mini, 8 sec., 90%
Substrate	aluminium
Surface	sanded
Thickness	4 mm



Typical type of failure




Further characteristics*


Salt spray tests	–
Static load	–
Torque out:	–

- Fluid susceptibility acc. DO 160 G Sec 11.4 (material)
- Flammability in acc. FAR 25-60 sec. vert. (material)


Load case



Pull-off



Shear



Permanent load

* Not all characteristics apply to all combinations available